## IN THE CLAIMS

The following claim set replaces all prior versions, and listings, of claims in the application:

- (currently amended) A laser weldable resin composition comprising (A) 100 parts by weight of a polybutylene terephthalate-series resin, (B) 1 to 50 parts by weight of an elastomer, (C) 5 to 100 parts by weight of a polycarbonate-series resin, and (D) 1 to 10 parts by weight of a plasticizer, wherein
  - the polybutylene terephthalate-series resin (A) comprises a polybutylene

    terephthalate-series copolymer modified with not more than 30% by mol of
    a copolymerizable monomer, and wherein
  - the elastomer (B) comprises at least one member selected from the group consisting of a polystyrene-series elastomer and a polyester-series elastomer, and wherein
  - the plasticizer (D) comprises at least one member selected from the group consisting of an aromatic polycarboxylic acid ester and an acrylic polymer.
- 2. (canceled)
- 3. (original) A resin composition according to claim 1, wherein the refractive index of the elastomer (B) is 1.52 to 1.59 at a temperature of 25°C.
- 4. (cancelled)
- 5. (original) A resin composition according to claim 1, wherein the refractive index of the plasticizer (D) is 1.45 to 1.60 at a temperature of 25°C.
- 6. (cancelled)
- 7. (original) A resin composition according to claim 1, which further comprises (E) a filler or reinforcing agent.

**SAKATA et al Serial No. 10/574,574**December 11, 2008

- 8. (original) A resin composition according to claim 7, wherein the filler or reinforcing agent (E) is vitreous or glassy.
- 9. (original) A resin composition according to claim 1, which further comprises (F) a nucleating agent.
- 10. (original) A resin composition according to claim 1, wherein when a light having a wavelength of 800 to 1200 nm is irradiated to a molded product of 80 mm in length, 80 mm in width and 2 mm in thickness formed from the resin composition by an injection molding, the fluctuation range of light transmittance depending on sites to be irradiated of the molded product is not more than 10%.
- 11. (original) A molded product formed from a resin composition recited in claim 1.
- 12. (original) A composite molded product comprising a molded product formed from a resin composition recited in claim 1 and a counterpart resin molded product, wherein the molded product is bonded to the counterpart molded product by a laser welding.
- 13. (original) A process for producing a composite molded product, which comprises contacting a molded product formed from a resin composition recited in claim 1 and located in a transmitting side for a laser beam, with a counterpart resin molded product located in a receiving side for the laser beam, and irradiating the laser beam to these articles for bonding the molded product to the counterpart molded product.